



UNA EMPRESA ARGENTINA A SU SERVICIO

COMPOSICIÓN QUÍMICA ÁNODOS DE COBRE

Fabricación Copper Metal S.A.I.C.



COMPOSICIÓN QUÍMICA

	Cu %	Sn %	Pb %	Fe %	Al %	As %	P %	Mn %	Ni %	Si %	Zn %
min/max	99.9	< 0.01	< 0.01%	< 0.01%	< 0.01	< 0.005	0.045 - 0.06%	< 0.001	< 0.006	< 0.005	< 0.02

NORMAS APLICABLES PARA SU FABRICACIÓN

Denominación	Liga ASTM/UNS	Cu %	Fe %	Al %	P %	Mn %	Si %	Otros	Zn %
Cobre electrolítico	C11000	99,9 min							
Cobre fosforoso (DLP)	C12000	99,9 min			0.004 0.012				
Cobre fosforoso (DHP)	C12200	99,9 min			0.015 0.04				

📍 Cerrito 3480, B1752AEJ Lomas del Mirador, Provincia de Buenos Aires

✉️ consultas@coppermetal.com.ar

📞 011 6390 0877

📞 011 4482-6162 / 4651-1986 / 4651-1166

🌐 <https://www.coppermetal.com.ar/>

